



TECHNICAL DATA SHEET

ROOFBOND BITUPRIME - NIF

DESCRIPTION: ROOFBOND BITUPRIME is a copolymer acrylic, blended with bitumen. Designed primarily for resurfacing decramastic roofs. This cross-linking feature will also act as a self-repairing mechanism making this product ideal for a roof coating. This waterproofing membrane has an inbuilt anti-corrosive and adhesion. It is ideal as a metal roof primer with very good dirt resistance, while allowing water vapour permeability.

RECOMMENDED USE: ROOFBOND BITUPRIME Primer is a first coat primer and has excellent chip holding properties, boasts fast drying properties and offers excellent adhesion. Its remarkable flexibility ensures durability and resilience. Moreover, its water washup feature adds convenience to the application process.

APPLICATION PROCESS: Remove all mold with Shieldcoat Mossy, Waterblast roof with 3000psi minimum. Apply one coat of **Bituprime**, apply chippy while wet. Once cured, remove loose chip, apply Roofbond matt finish.

APPLICATION DETAILS / GUIDE:

Application method: Airless spray / Brush / Roller

Thinner: Not recommended (use Shieldcoat Hot Weather Additive sparingly)

Airless Tip Size: 517 - 521

Clean up: Water

Indicated film thickness: 175 microns (WFT)

Indicated film thickness: 95 microns (DFT)

Coats Required: 1 (Minimum)



TECHNICAL DATA SHEET

ROOFBOND BITUPRIME - NIF

TYPICAL PROPERTIES:

Colour: Wide range of factory and custom colours

Finish: Gloss

Size: 15 Ltr

Volume solids: 50% average**

Theoretical spreading rate: Asbestos Roof 5m² / Litre

Application surface temperature: 10°C to 40°C

Touch Dry: 30 minutes*

Recoat: 2 hours *

Full Cure: 10-14 days*

Drinking Water Safe: After 10 days* curing and initial rinse (rain or garden hose pressure).

Shelf life: 24 Month

*All figures are quoted at 25° Celsius and 50% Relative Humidity

Solid content, weight % : 62 ± 1

Minimum Viscosity at 30°C

Brookfield RVT, 2 /20, Ps : 2 – 10

pH (1:1 with water) : 5.5 – 7



TECHNICAL DATA SHEET

ROOFBOND BITUPRIME - NIF

HEALTH AND SAFETY:

Contact The Poisons Information Center on Phone: 0800 764 766 or a doctor.

Ingestion: Do not induce vomiting. Give water to drink. Seek medical assistance.

Eye Contact: Flush eyes using eye baths until irritation subsides. Seek medical assistance.

Inhalation: Remove to fresh air. Seek medical assistance

Skin Contact: Wash thoroughly with soap and water. Launder clothing before reuse. Seek medical assistance if irritations persist.

Medical attention: Treat symptomatically.

First Aid Facilities: Eye Baths, safety showers.

RECOMMENDATIONS AND PRECAUTIONS:

Ensure that appropriate workplace health and safety methods and PPE are used when working with this product.

Ventilation: Ensure adequate ventilation when using this product.

Drinking water: When drinking water collection systems are in place, Shieldcoat recommends disconnecting the system prior to commencing work, then allowing 10 days of curing and a thorough fresh water rinse (rain or garden hose pressure) before reconnecting the system. Ensure that this product is applied in full accordance with Shieldcoat Recommendations.

Care and Maintenance: Protect the coating from abrasive contact for 10 days. Wash down periodically with a mild detergent solution to refresh and preserve the coating.

MSDS: Available on request or download from the Shieldcoat website. www.shieldcoat.co.nz

DISCLAIMER: Shieldcoat advises that the applicator of this product is responsible to determine and verify its suitability for the intended use prior to application. The data and recommendations contained within this document were true and accurate at the time of writing.